

SPATOLATO GRANELLO ACRILICO

ALGAE INIBITOR

Coating thickness
FOR INDOOR AND OUTDOOR USE

DECORA SYSTEM



Continuous coating thickness, based on acrylic resins in emulsion, inorganic pigments, quartz and balanced grain size, so as to achieve a pleasing aesthetic effect full and continuous. SPATOLATO GRANELLO allows to eliminate any imperfections in the surface.

Type of support:

traditional or pre-mixed plasters, old painted plaster, prefab in concrete and precast cladding systems "DECOKLIMA".

Preparation:

all surfaces must be dry, clean thoroughly. In the case of chalk (plaster), or flaking (Old paint) we suggest you to restore the integrity of the support through mechanical scraping or pressure washing. Always apply a hand of primer PLIOFLEX Decora (see data technique) and a hand of undercoat MUROBELLO.

Precautions:

Unsuitable weather conditions can adversely affect drying's time, compromising product's performance and his aesthetic. It is therefore recommended to use the product on the climatic conditions outlined below. The polymerization process occurs in 15 days under optimal conditions (20 °C 60% RH). If heavy rains occurs first the unprotected paint is completely dry could highlight ugly-looking flaws. In case of occurrence of this phenomenon wet immediately throughout the area where lies the painting without scrubbing or wait for the next rainfall event. It strongly recommended not to repaint the area affected by the problem before the flaw's disappear.

Packaging: 25 Kg

Available colors:

White and color chart
COLLEZIONE 1000 and
COLLEZIONE 2000

Composition:

inorganic pigments, marble's grits, dispersed quartz in acrylic resin in water emulsion. Addition of biocides broad-spectrum biocides fits for the sustainable conservation of the product and the prevention of fungus, algae and mold on the wall.

Labelling:

In accordance with EC Regulation 1272/2008 (CLP), the preparation is labeled as follows: see MSDS.

Type of waste:

Empty bucket: special or similar to urban.
Bucket with waste: special.

Storage:

min T°: 5°C, max T°: 30°C.

Stability:

APPLICATION



METAL TROWEL, PLASTIC TROWEL.

How to use:

Spread onto the substrate using metal trowel. Finish with plastic or steel trowel in a circular direction. Always work in full the walls, in order to avoid unaesthetic differences of color. Avoid applying in direct sunlight and in the presence of strong wind.

www.coloridecora.it

COLORI DECORA Srl.
BASTIA UMBRA/PERUGIA
06083 Zona Ind.le - via degli Olmi, 10
Tel. 075 - 800 45 64 - Fax 075 - 800 48 76
e-mail: decora@coloridecora.it



SPECIFICATIONS:

Environmental conditions:	T°min: 5°C •T°max: 30° C •U.R.max: 65%
Drying:	DRY SURFACE: 3-6h COMPLETELY DRY: 24-48h
Appearance:	MATT
Specific gravity:	1,67 kg/L +/- 0,03
Solids content:	76% +/- 2
PH:	8-8,5
Alkali resistance (UNI10795):	ALKALI RESISTANT PAINT
Dilution:	READY TO USE, Do not subject to agitation of mechanical mixers
GRAIN 1,2 consumption:	1,8 Kg/m ²
GRAIN 1,5 consumption:	2,4 Kg/m ²
GRAIN 2,5 (only on request) consumption:	3,0 Kg/m ²

360 days in the original containers

The above technical information are the result of accurate laboratory tests and practical experience. However, since the product is often used outside our control, we can not guarantee that the quality. This information is subject to possible updates from the company